



Rare Earth Elements (REE) Extraction from The Stones Hill at Padang Area by Precipitation

Oknovia Susanti^{1*}, Zeky Azizi¹

¹Faculty of Engineering, Andalas University, Limau Manis, Padang, Indonesia

Received: March 16, 2024

Revised: May 07, 2024

Accepted: July 25, 2024

Published: July 31, 2024

Corresponding Author:

Oknovia Susanti

oknovia.s@eng.unand.ac.id

DOI: [10.29303/jppipa.v10i7.8277](https://doi.org/10.29303/jppipa.v10i7.8277)

© 2024 The Authors. This open access article is distributed under a (CC-BY License)



Abstract: Rare Earth Elements (REE) are a very important element in modern life such as electronics, materials engineering, and even medicine. Gadolinium (Gd) is one of the REEs that is used as a basic material for implants as well as being used for other basic materials such as a corrosion inhibitor, control rods for nuclear reactors, and others. In this case, the elements are found along hills in the Padang area which have the potential to be produced in large quantities from six rock minerals such as granite, basalt, clay, silica, tuff, and limestone. Based on the results of identification using the XRF spectrometer test tool, it was found that the six mineral rocks had an abundance of rare earth elements. The results of testing the extraction of Gadolinium Oxide (Gd₂O₃) using XRF were successfully carried out, Gd₂O₃ can be extracted by 0.06% - 1.84% in basalt rock, 0.47% - 0.95% in clay rock, and 0% - 0.88% in silica rock. This proves that the main rock minerals from stones have the Rare Earth Elements (REE) and can be extracted with using the Precipitation Extraction method.

Keywords: Basalt; Clay; Extraction; Gadolinium; Granite; Limestone; Rare Earth Metal (REM); Silica; Tuff; XRF Spectrometer.

Introduction

The use of rare-earth elements triggers the development of new material technologies (Klinger, 2018). The utilization of rare earth elements is needed in the large various fields from the electronics industry to the modern transportation industry and also the development of material processing technology, potentially in high technology industries (Filho et al., 2023). REE also plays a very important role in the needs of modern production materials such as in the world of superconductors, lasers, electronic optics, LED and iPad applications, glass, and ceramics (Henderson, 1984)(Aide, 2023). In the future, it is estimated that the use of rare earths will expand, especially single rare earth elements, such as neodymium, samarium, europium, gadolinium, and yttrium. (Randive et al., 2014; Aldila et al., 2024; Sapulete et al., 2023)

Rare earth Elements (REE) are found in complex compounds. The content of REE is found in granite because carbonatic deposits are also followed by the

formation of granite rocks (Muecke et al., 1979; Humphris & E, 1984). Other mineral rocks such as basalt rock, tuff rock (tuffaceous mineral), silica mineral rock, limestone (limestone), and clay rock (clay) are also indicated to contain REE (Lee & Tanaka, 2021; Arsyad et al., 2022). The REE has found potential in Sumatera, which is part of Indonesia, especially in hilly areas. So far, the production of rare earth elements in Sumatra has been exploited in Bangka Belitung. And then the REEs are processed by extracting and refining because their chemical properties are similar and difficult to separate from each other (Syaeful et al., 2014; Tirono, 2022; Efendi et al., 2023). This process involves sophisticated chemical separation technologies (Anggara et al., 2018; Mulyono et al., 2023). Recently, the need for REE has increased, especially since that is used as degradable implant Material. Gd is one of the REEs which is used as a material to resist the corrosion rate of the alloys for an implant. Therefore, the exploitation of Gd had become a production target due to the need for implant materials (Susanti & Harjanto, 2019; Lu et al., 2022; Bian et al., 2018;

How to Cite:

Susanti, O., & Azizi, Z. (2023). Rare Earth Elements (REE) Extraction from The Stones Hill at Padang Area by Precipitation. *Jurnal Penelitian Pendidikan IPA*, 10(7), 3968–3974. <https://doi.org/10.29303/jppipa.v10i7.8277>

Tong et al., 2022). Gadolinium is one element that has the potential to be used as an implant material. This element is combined with Mg which aims to slow down the corrosion of the Mg element. This element comes from rocks that are processed through filtering to get pure Gd (Rahayu et al., 2023)

Gadolinium

Gadolinium is found in several other minerals, including monazite and bastnasite (Kanazawa & Kamitani, 2006; Balaram, 2019). Gadolinium is a chemical element in the periodic table of elements having the symbol Gd and atomic number 64, which is a very strong paramagnetic element that is an important requirement for contrast compounds and has a very high absorption capacity of neutrons. Gadolinium is a rare earth element that significantly improves the mechanical properties and creeps resistance of magnesium through processing at high temperatures and also improves solid solution strengthening and precipitation hardening (Gao et al., 2009; Kong, 2017). Gadolinium can contribute to recrystallization (Mouhib et al., 2024). As a material for implants, a ductile material that is easily formed is required to produce a variety of components according to the damaged bone tissue. The addition of gadolinium to magnesium greatly affects grain size and texture (Susanti et al., 2020). Gadolinium can enhance the performance of iron, chromium, and related alloys, as well as increase resistance to oxidation at concentrations of <1% (Affi; et al., 2023; Susanti & Harjanto, 2019).

Mineral Rocks of the Hills at Padang Area

Along with the Hills Padang area has six main mineral rocks, namely granite, basalt, clay, silica, tuff, and limestone (Rahmi & Helendra, 2018). Rock Granite is a coarse-textured acid igneous rock Granite is part of the granitoid rock group and includes acid igneous rocks with characteristics composed of crystals of coarse size and phaneritic-porphyritic granularity. The S-type granite rock in the northern part of Bangka Island (Kabat Granite) is one type of granite rock that is rich in REM content (Zulfikar et al., 2020). Based on data from the Mining Bureau of PT. Semen Padang, granite rock contains a chemical composition of 72.6% SiO₂, 18.1% Al₂O₃, 1.3% CaO, and 0.6% MgO. Basalt is a volcanic igneous rock that generally has a smooth (aphanitic) and holocrystalline texture. Based on data from the Mining Bureau of PT. Semen Padang basalt rock contains 62.0% SiO₂, 19.9% Al₂O₃, 3.6% CaO, and 0.7% MgO. Clay rocks are also called clay stones. Clay minerals are a group of minerals that make up sedimentary rocks. Granitoid rocks contain completely weathered REM deposits and almost all REM is concentrated in the form of a clay layer on the weathered crust (Anshori, 2007).

Based on data from the Mining Bureau of PT. Semen Padang, clay rock contains a chemical composition of 54.17% SiO₂, 21.94% Al₂O₃, 0.26% CaO, and 0.51% MgO. Silica in nature comes from igneous rocks and metamorphic rocks which are destroyed by weathering processes, and undergo transportation and deposition. Based on data from the Mining Bureau of PT. Semen Padang, silica rock contains a chemical composition of 67.6% SiO₂, 19.0% Al₂O₃, 0.2% CaO, and 0.2% MgO. Tuff rock stone is divided into two types, namely white tuff and red tuff. Granitic instrumentations pierce the mapped tuffs. Mineralization in mineral-rich tuff deposits that carry REM Zr-Nb. Based on data from the Mining Bureau of PT. Semen Padang, tuff rock contains a chemical composition of 79.13% SiO₂, 6.49% Al₂O₃, 5.56% CaO, and 1.27% MgO. Limestone or limestone, also known as limestone, is an important ingredient in cement production. Limestone Karts mineral deposits have monazite mineral density. Based on the latest data from the Mining Bureau of PT. Semen Padang, limestone contains a chemical composition of 2.2% SiO₂, 0.5% Al₂O₃, 53.7% CaO, and 0.5% MgO.

REE Processing

Rare earth elements processing from rare earth carrier minerals can be carried out using extraction, such as H₂SO₄ solvent precipitation extraction, REM-Oxalate feed extraction, and n-hexane solvent extraction. REM processing can also be done through the beneficiation process of Rare Earth Metal (REM) carrier minerals (Thomas et al., 2024; Trisnawati et al., 2020; Talens-Peiró & Villalba Méndez, 2013).

REM Extraction

Extraction is the process of separating materials from the mixture using a suitable solvent. After the extraction process, the solvent is separated from the sample by filtration (Nascimento et al., 2020). Extraction in general is a process of separating the active substance from a solid or a liquid using a solvent (Zhang et al., 2018; Patel et al., 2019). The choice of solvent is needed in the extraction process because the solvent used must be able to separate or extract the desired substance without dissolving other unwanted substances (Dulanlebit & Hernani, 2023). The refining process of REE can be carried out in various ways, namely extraction, ion exchange resin, and precipitation. (El-Ouardi et al., 2023) The digestion process is carried out using concentrated H₂SO₄ which breaks down the structure of the sample and precipitates refractory metals such as iron, aluminum, copper, and chromium. Destruction results in the form of sediment and filtrate (Balaram & Subramanyam, 2022). The addition of

hydrogen peroxide to the digestive filtrate aims to optimize the solubility of REM. The filtrate is added with NH_4OH (ammonia) reagent. The commonly used precipitation reagents are NH_4OH and NaOH . The advantages of using NH_4OH are easy handling and cheaper price (Nadiatul & Zainal, 2017; Susanti et al., 2015; Zakiyuddin et al., 2020).

REE Beneficiation

The beneficiation process is also called the process of physically increasing the levels of oxide compounds (Rodliyah et al., 2021). The REE beneficiation process is an increase in the levels of REE oxide compounds in rare earth metal carrier minerals (Jordens et al., 2013). The shaking table is a material separation device by flowing thin water (Flowing Film Concentration) to the mineral carrying REE. On a rocking table equipped with a refile (barrier). Factors that can affect the performance of the Shaking Table are the size of the feed, Operational (roughing/cleaning), and the specific gravity differences. Mineral concentration carried out by gravity (Gravity Concentration) is the separation of minerals that depend on the difference in density (density), the shape and size of the density difference with the estimated mineral concentration criteria (Nadiatul & Zainal, 2017; Borisov, 2019).

Method

Materials and Equipment

The materials used in the research were granite, basalt, clay, silica, tuff, and limestone 120 mesh, concentrated H_2SO_4 (98%), 20% H_2SO_4 , 25% NH_4OH , 3% H_2O_2 , and Aquades (Suparno & Simamora, 2023). The type of chemical used is chemical Pro Analysis (PA). Samples and extraction results were tested using the PAN analytical Epsilon 3 Spectrometer XRF device. The tools used were the Pulverisette 6 Classic Line Fritsch Planetary Mono Mill Ball mill, Analytical scales, measuring cups, reflux flasks, heating mantles, 125 mm Whatman Ashless filter paper, Magnetic stirrer, oven, as well as research support tools such as drop pipettes, stirring rods, glass funnels, and others.

Collection and Sample Preparation

The Gd extraction process can be seen in Figure 1. Rock samples were taken at one of the Hills Padang areas. A sampling of granite, basalt, clay, silica, tuff, and limestone was carried out three times at different points in the Padang area mining area. After the sample is taken the sample is crushed into small gravel, then dried under the sun, after drying the sample is ground using a ball mill at a speed of 200 rpm for 15 minutes per sample and repeated until a fine sample is obtained which is

sufficient for extraction. Extracted fine samples are filtered using a 120-mesh sieve until a fine 120 mesh sample is obtained which is ready to be tested at extraction stages.

Extraction (Separation) of REE

A total of 20 grams of 120 mesh fine rock powder samples from each rock mineral was put into a reflux flask, 40 ml of concentrated H_2SO_4 slowly added, and stirred until well blended. To the mixture, add 100 ml of Aquades and 5 ml of 20% H_2SO_4 slowly, stirring until evenly distributed and allowed to cool. After chilling, the mixture was heated to boiling ($\pm 130^\circ\text{C}$ - 150°C), then allowed to cool in a fume hood, after cooling the solution was filtered using 125 mm Whatman Ashless paper. The results of filtering produce filtrate and sediment. The filtrate was added with 50 ml of 3% H_2O_2 , and 70 ml of 25% NH_4OH , then stirred using a Magnetic Stirrer ± 30 minutes at a speed of 240 rpm. Furthermore, the filtrate is allowed to stand in a fume hood for ± 3 days until REE crystal oxide precipitate is formed. The precipitate was filtered using Whatman Ashless paper and dried in an oven at 100°C for 1 hour. The dry crystalline precipitate is allowed to stand and mashed. The final result is the fine REE oxide analyzed using an XRF spectrometer. (Dulanlebit & Hernani, 2023; S, 2022)




Figure 1. Processing of REE filter

Results and Discussion

The extraction method was carried out on the six rock mineral powders of Granite, Basalt, Clay, Silica, Tuff, and Limestone with a fine powder of 120 mesh. The extraction was carried out three times per rock mineral sample according to the sampling. Based on the results of the extraction of 20 grams of rock samples, it was found that the extraction method of deposition succeeded in forming REE oxide crystals on three mineral rocks, namely basalt, clay, and silica. Meanwhile, REE crystal oxide deposits in granite, tuff, and limestone rock minerals are not formed. Gadolinium has been successfully extracted from basalt, clay, and silica minerals. The extracted REM oxide deposits do not form in granite, tuff, and limestone minerals. Based on (Arianto et al., 2020) this can be caused by the unsuitable H₂SO₄ solvent so that it cannot digest REM minerals. Based on the extraction data, from 100% of the total rare earth in the final REE oxide deposition analyzed after separation or extraction, it can be seen that the percentage of Gadolinium increases compared to the initial identification data before extraction. The largest percentage of Gadolinium obtained was 1.835% in basalt rock mineral sample 2, while the smallest was found in sample 1 silica at 0%. On the other hand, the elements that are also effectively attracted are Terbium (Tb) and Europium (Eu). The XRF test results of the extracted REE crystal oxide precipitate can be seen in Table 1.

Table 1. The Extracted REE Precipitated Oxide

RE M Oxi des	Basalt			Clay			Silica		
	Sample (%)			Sample (%)			Sample (%)		
Y ₂ O ₃	0	0.1	0.	0.4	0.2	0.	0	0.2	0.3
		6	15	6	9	26	0	7	3
La ₂ O ₃	0	0	0	0	0	0.	0.9	0	0
						48	9		
Nd ₂ O ₃	1.	1.4	1.	0	0	0	2.2	0.5	2.8
	4	5	47				7		2
Eu ₂ O ₃	0.	0.7	0.	0.7	0.4	0.	1.3	0.6	1.5
	97	3	73	8	9	51	9	9	5
Gd ₂ O ₃	0.	1.8	1.	0.4	0.9	0.	0	0.8	0.3
	06	3	82	7	4	68	0	7	5
Tb ₄ O ₇	97	95.	95	97.	98.	9.	94.	97.	94.
	.3	81	.8	66	21	98	32	44	86
Lu ₂ O ₃	0.			0.6			1.0		0
	25	0	0	11	0	0	7	0	0

The precipitation extraction method using concentrated sulfuric acid solvent can extract the elements Yttrium (Y), Lanthanum (La), Neodymium (Nd), Europium (Eu), Gadolinium (Gd), Terbium (Tb), and Lutetium (Lu). Comparison of the extraction yield

of Poboya gold tailings with mineral rock from one of the hills at Padang Area such as Karang Putih Mine of PT. Semen Padang can be seen in Table 2.

Table 2. Comparison of the Extraction Result of Precipitation Method

REM	Poboya Gold Tailings	Mineral Rocks Karang Putih Mining		
		Basalt	Clay	Silica
Average (%)		Average (%)		
La	13.49	0	0.16	0.33
Nd	0.02	1.44	0	1.86
Eu	4.84	0.81	0.59	1.21
Gd	0.02	1.24	0.69	0.41
Tb	78.98	9.630	9.79	95.54




Figure 2. Gadolinium Extraction Result Diagram

Based on (Arianto et al., 2020) using the precipitation extraction method, the concentration of Gadolinium after extraction is 0.02% and Terbium can be extracted from 77.82% - 80.06%. Compared with the extraction results, the researchers obtained that the concentration of Gadolinium after extraction was 1.241% for basalt rock minerals, 0.69% for clay rock minerals, and 0.4103% for silica rock minerals, and Terbium (Tb), which is 94.33% - 98.22%. Based on the results obtained by the researchers, this proves that the precipitation extraction method is more effective and suitable for basalt, clay, and silica rock minerals. On the other hand, the precipitation extraction method is also very effective for extracting the Terbium (Tb) element, which is 94.33% - 98.22% and the Europium (Eu) element is 0.49% - 1.55%. This proves that the precipitation extraction method with concentrated sulfuric acid solvent is suitable for basalt rock, clay, and silica minerals for the extraction of the elements Terbium (Tb), Europium (Eu),

and Gadolinium (Gd). A diagram of the results of Gadolinium extraction from basalt, clay, and silica can be seen in Figure 2.

Conclusion

Gadolinium was successfully extracted using precipitation extraction methods in basalt, clay, and silica minerals. The results of testing the extraction of Gadolinium Oxide (Gd₂O₃) using XRF were successfully carried out, Gd₂O₃ can be extracted by 0.06% - 1.84% in basalt rock, 0.47% - 0.95% in clay rock, and 0% - 0.88% in silica rock. This proves that the main rock minerals from stones have the Rare Earth Elements (REE) and can be extracted with using the Precipitation Extraction method.

Acknowledgments

The authors would like to thank Lab. Metallurgy and Lab Chemistry, Universitas Andalas for supporting this material and his laboratory facilities.

Author Contributions

Conceptualizing research ideas, O. S; research methodology, O. S, Z. A; data analysis, O. S; securing funding, O. S; writing original drafts, O. S; Z. A; management responsibilities, O. S; coordination for research planning and implementation of activities, O. S, Z. A.

Funding

This work was supported by Publication Grant Universitas Andalas, (Hibah Publikasi Fakultas).

Conflicts of Interest

The authors declare no conflict of interest, financial or otherwise.

References

- Affi, J., Susanti, O., Yanda, H., Azizi, Z., & Devilla, R. (2023). Identification of Rare Earth Elements (REE) from granite, basalt, clay, silica, and limestones at Padang Regions. *AIP Conference Proceedings*. AIP Publishing, 2592(1). <https://doi.org/https://doi.org/10.1063/5.0140397>
- Aide, M. (2023). Rare Earth Elements - Emerging Advances, Technology Utilization, and Resource Procurement. *IntechOpen*, 102266. <https://doi.org/10.5772/intechopen.102266>
- Aldila, H., Indriawati, A., & Putro, P. A. (2024). Purification and Characterization of Monazite from Bangka using Mechanical-Magnetic Separation Method. *Jurnal Penelitian Pendidikan IPA*, 10(5), 2745-2751. <https://doi.org/10.29303/jppipa.v10i5.6644>
- Anggara, F., Amijaya, D. H., Harijoko, A., Tambaria, T. N., Sahri, A. A., & Asa, Z. A. N. (2018). Rare earth element and yttrium content of coal in the Banko coalfield, South Sumatra Basin, Indonesia: Contributions from tonstein layers. *International Journal of Coal Geology*, 196(July), 159-172. <https://doi.org/10.1016/j.coal.2018.07.006>
- Anshori, C. (2007). Petrogenesis Basalt Sungai Medana Karangsembung, Berdasarkan Analisis Geokimia. *Jurnal Riset Geologi & Pertambangan Jilid 17*, 1(1), 37-50. Retrieved from https://jrisetgeotam.lipi.go.id/index.php/jrisgeotam/article/download/143/pdf_9
- Arianto, Sosidi, H., Prismawiryanti, & Pusptasari, D. J. (2020). Pemisahan Logam Tanah Jarang dari Limbah (Tailing) Emas Poboya dengan Metode Pengendapan. *KOVALEN: Jurnal Riset Kimia*, 6(1), 9-17. <https://doi.org/10.22487/kovalen.2020.v6.i1.13861>
- Arsyad, M., Rukmana, M., & Palloan, P. (2022). Valuation of Physical Properties of Rocks in the Maros Pangkep Karst Area of Bantimurung Bulusaraung National Park. *Jurnal Penelitian Pendidikan IPA*, 8(4), 1954-1962. <https://doi.org/10.29303/jppipa.v8i4.1960>
- Balaram, V. (2019). Rare earth elements: A review of applications, occurrence, exploration, analysis, recycling, and environmental impact. *Geoscience Frontiers*, 10(4), 1285-1303. <https://doi.org/10.1016/j.gsf.2018.12.005>
- Balaram, V., & Subramanyam, K. S. V. (2022). Sample preparation for geochemical analysis: Strategies and significance. *Advances in Sample Preparation*, 1(December 2021), 100010. <https://doi.org/10.1016/j.sampre.2022.100010>
- Bian, D., Deng, J., Li, N., Chu, X., Liu, Y., Li, W., Cai, H., Xiu, P., Zhang, Y., Guan, Z., Zheng, Y., Kou, Y., Jiang, B., & Chen, R. (2018). In Vitro and in Vivo Studies on Biomedical Magnesium Low-Alloying with Elements Gadolinium and Zinc for Orthopedic Implant Applications. *ACS Applied Materials and Interfaces*, 10(5), 4394-4408. <https://doi.org/10.1021/acsami.7b15498>
- Borisov, V. A., Rozhkov, N. N., Ponyatova, S. S., Bogdanova, A. O., Adeeva, L. N., & Krugley, A. O. (2019). The recovery of rare earth concentrate from spent cracking catalyst. *AIP Conference Proceedings*, 2141, 020025. <https://doi.org/10.1063/1.5122044>
- Dulanlebit, Y. H., & Hernani, H. (2023). Overview of Extraction Methods for Extracting Seaweed and its Applications. *Jurnal Penelitian Pendidikan IPA*, 9(2), 817-824. <https://doi.org/10.29303/jppipa.v9i2.3053>

- Efendi, Y. R., Suprayitno, E., & Hariati, A. M. (2023). Profile of Amino Acids and Proximate on the Extraction of Red Ginger Protease Enzymes in Commercial Feed for Aquaculture. *Jurnal Penelitian Pendidikan IPA*, 9(9), 6757–6764. <https://doi.org/10.29303/jppipa.v9i9.4141>
- El-Ouardi, Y., Virolainen, S., Massima Mouele, E. S., Laatikainen, M., Repo, E., & Laatikainen, K. (2023). The recent progress of ion exchange for the separation of rare earths from secondary resources – A review. *Hydrometallurgy*, 218(May 2022), 106047. <https://doi.org/10.1016/j.hydromet.2023.106047>
- Filho, W. L., Kotter, R., Özuyar, P. G., Abubakar, I. R., Eustachio, J. H. P. P., & Matandirotya, N. R. (2023). Understanding Rare Earth Elements as Critical Raw Materials. *Sustainability (Switzerland)*, 15(3). <https://doi.org/10.3390/su15031919>
- Gao, L., Chen, R. S., & Han, E. H. (2009). Effects of rare-earth elements Gd and Y on the solid solution strengthening of Mg alloys. *Journal of Alloys and Compounds*, 481(1–2), 379–384. <https://doi.org/10.1016/j.jallcom.2009.02.131>
- Henderson, P. (1984). *Rare Earth Element Geochemistry*. USA: Elsevier.
- Humphris, S. E. (1984). The mobility of the rare earth elements in the crust. In *Rare Earth Element Geochemistry*, 2, pp. 317–342). Elsevier. <https://doi.org/10.1016/B978-0-444-42148-7.50014-9>
- Jordens, A., Cheng, Y. P., & Waters, K. E. (2013). A review of the beneficiation of rare earth element bearing minerals. *Minerals Engineering*, 41, 97–114. <https://doi.org/10.1016/j.mineng.2012.10.017>
- Kanazawa, Y., & Kamitani, M. (2006). Rare earth minerals and resources in the world. *Journal of Alloys and Compounds*, 408–412, 1339–1343. <https://doi.org/10.1016/j.jallcom.2005.04.033>
- Klinger, J. M. (2018). Rare earth elements: Development, sustainability and policy issues. *Extractive Industries and Society*, 5(1), 1–7. <https://doi.org/10.1016/j.exis.2017.12.016>
- Kong, L. (2017). Two main and a new type rare earth elements in Mg alloys: A review. *IOP Conference Series: Materials Science and Engineering*, 242(1). <https://doi.org/10.1088/1757-899X/242/1/012026>
- Lee, S., & Tanaka, T. (2021). Gd matrix effects on Eu isotope fractionation using MC-ICP-MS: Optimizing europium isotope ratio measurements in geological rock samples. *International Journal of Mass Spectrometry*, 469, 116668. <https://doi.org/10.1016/j.ijms.2021.116668>
- Lu, Y., Huang, Y., Bode, J., Vogt, C., Willumeit-Römer, R., Kainer, K. U., & Hort, N. (2022). Effects of Minor Gadolinium Addition and T4 Heat Treatment on Microstructure and Properties of Magnesium. *Advanced Engineering Materials*, 24(12). <https://doi.org/10.1002/adem.202200966>
- Mouhib, F., Gao, B., & Al-Samman, T. (2024). On the role of selective nucleation and growth to recrystallization texture development in a Mg–Gd–Zn alloy. *Journal of Materials Science*, 59(3), 1044–1055. <https://doi.org/10.1007/s10853-023-09243-3>
- Muecke, G. K., Pride, C., & Sarkar, P. (1979). Rare-earth element geochemistry of regional metamorphic rocks. *Physics and Chemistry of the Earth*, 11(C), 449–464. [https://doi.org/10.1016/0079-1946\(79\)90043-0](https://doi.org/10.1016/0079-1946(79)90043-0)
- Mulyono, A., Setiawan, I., Hidayat, E., & Noviard, R. (2023). Distribution and potential contamination assessment of rare earth elements (REE) in Indonesian volcanic soil. *Acta Ecologica Sinica*, August. <https://doi.org/10.1016/j.chnaes.2023.05.010>
- Nadiatul, N., & Zainal, S. (2017). The evolution of mineral processing in extraction of rare earth elements using solid-liquid extraction over liquid-liquid extraction: A review. *Minerals Engineering*, 112(March), 103–113. <https://doi.org/10.1016/j.mineng.2017.07.014>
- Nascimento, M., Vera, Y. M., Valverde, B. M., & Gomes, R. de C. (2020). Separation of rare earths by solvent extraction using DEHPA. *Brazilian Applied Science Review*, 4(3), 1697–1706. <https://doi.org/10.34115/basrv4n3-076>
- Patel, K., Panchal, N., & Ingle, P. (2019). Review of Extraction Techniques Extraction Methods: Microwave, Ultrasonic, Pressurized Fluid, Soxhlet Extraction, Etc. *International Journal of Advanced Research in Chemical Science*, 6(3), 6–21. <https://doi.org/10.20431/2349-0403.0603002>
- Rahayu, P. P., Widyastuti, E. S., Nurwahyuni, E., Yunita, C. N., & Hakim, L. (2023). Characterization of Andrographis Paniculata Extract Obtained by Microwave-Assisted Extraction (MAE) Method with Radiation Time. *Jurnal Penelitian Pendidikan IPA*, 9(12), 11289–11295. <https://doi.org/10.29303/jppipa.v9i12.5624>
- Rahmi, A., & Helendra, H. (2018). Relationship Between the Clay Composition and the Soil Source in West Sumatera. *Jurnal Penelitian Pendidikan IPA*, 5(1). <https://doi.org/10.29303/jppipa.v5i1.152>
- Randive, K., Kumar, J. V., Bhondwe, A., & Lanjewar, S. (2014). Understanding the behaviour of rare earth elements in minerals and rocks. *Gondwana Geological Magazine*, 29(1–2), 29–37. Retrieved from <https://www.researchgate.net/publication/2753>

- 37571
Rodliyah, I., Wijayanti, R., Hidayat, K. N., Dianawati, E. A., Sudrajat, A., & Firmansyah, D. (2021). Beneficiation of cassiterite from primary tin ores using gravity and magnetic separation. *IOP Conference Series: Earth and Environmental Science*, 882(1). <https://doi.org/10.1088/1755-1315/882/1/012008>
- S, A. H. (2022). Characterization of PVA-Enzyme Coated Indicator Electrodes GA coated again with PVC-KTpCIPB-o-NPOE SEM-EDS, FTIR and XRD analysis. *Jurnal Penelitian Pendidikan IPA*, 8(1), 103–108. <https://doi.org/10.29303/jppipa.v8i1.1265>
- Sapulete, S. M., Souisa, M., Hanifah, A., & Papilaja, F. C. (2023). Analysis of Mountain Sand Material Content in Rumah Tiga and Hative Besar Villages, Teluk Ambon District Using X-Ray Diffraction (XRD) and X-Ray Fluorescence (XRF) Methods. *Jurnal Penelitian Pendidikan IPA*, 9(4), 1982–1986. <https://doi.org/10.29303/jppipa.v9i4.3168>
- Suparno, S., & Simamora, N. N. (2023). Effect Mass of Silica Sand on Reducing Fe Concentration in Water Purification Systems. *Jurnal Penelitian Pendidikan IPA*, 9(9), 7527–7532. <https://doi.org/10.29303/jppipa.v9i9.3416>
- Susanti, O., Affi, J., Asrilia, Y., Metalurgi, L., Mesin, J. T., Padang, U. A., Manis, K. L., Padang, K., & Barat, S. (2020). Pengaruh Komposisi Unsur Gadolinium (Gd) Terhadap Magnesium (Mg) Melalui Casting sebagai Bahan Dasar Implan: Kajian Literatur. *Jurnal Penelitian Enjiniring*, 24(2), 192–198. <https://doi.org/10.25042/jpe.112020.12>
- Susanti, O., & Harjanto, S. (2019). Corrosion behavior of hot rolled Mg-1 . 6Gd alloys as degradable materials implant Corrosion Behavior of Hot Rolled Mg-1 . 6Gd Alloys as Degradable Materials Implant. *AIP Conference Proceedings* 2180, 020052(December).
- Susanti, O., Harjanto, S., & Mochtar, M. A. (2015). Microstructure and Mechanical Properties of Extruded Mg-1.6Gd as Prospective Degradable Implant Materials. *Advanced Materials Research*, 1112, 462–465. <https://doi.org/10.4028/www.scientific.net/amr.1112.462>
- Syaeful, H., Setiawan, K. W., Sukadana, I. G., & Gunawan, A. M. (2014). Rare earth element exploration in Indonesia. In *Proceedings of Sundaland Resources 2014 MGEI Annual Convention*, pp. 17-18. Retrieved from [https://karya.brin.go.id/id/eprint/1005/1/PRO SIDING_SYAEFUL_MGEI_2014.pdf](https://karya.brin.go.id/id/eprint/1005/1/PRO_SIDING_SYAEFUL_MGEI_2014.pdf)
- Talens-Peiró, L., & Villalba Méndez, G. (2013). Material and energy requirement for rare earth production. *Jom*, 65(10), 1327–1340. <https://doi.org/10.1007/s11837-013-0719-8>
- Thomas, B. S., Dimitriadis, P., Kundu, C., Vuppaladadiyam, S. S. V., Raman, R. K. S., & Bhattacharya, S. (2024). Extraction and separation of rare earth elements from coal and coal fly ash: A review on fundamental understanding and on-going engineering advancements. *Journal of Environmental Chemical Engineering*, 12(3), 112769. <https://doi.org/10.1016/j.jece.2024.112769>
- Tirono, M. (2022). Effects of Exposure to Ultrasonic Waves on Extraction of Evaporation Methods on The Anthocyanin Content of Green Betal and Basil Leaves. *Jurnal Penelitian Pendidikan IPA*, 8(2), 599–604. <https://doi.org/10.29303/jppipa.v8i2.1368>
- Tong, X., Zhu, L., Wang, K., Shi, Z., Huang, S., Li, Y., Ma, J., Wen, C., & Lin, J. (2022). Impact of gadolinium on mechanical properties, corrosion resistance, and biocompatibility of Zn-1Mg-xGd alloys for biodegradable bone-implant applications. *Acta Biomaterialia*, 142(February), 361–373. <https://doi.org/10.1016/j.actbio.2022.02.015>
- Trisnawati, I., Prameswara, G., Mulyono, P., Prasetya, A., & Bayu Murti Petrus', H. T. (2020). Sulfuric Acid Leaching of Heavy Rare Earth Elements (HREEs) from Indonesian Zircon Tailing. *International Journal of Technology*, 11(4), 804–816. <https://doi.org/10.14716/ijtech.v11i4.4037>
- Zakiyuddin, A., Irawan, A. A., Susanti, O., & Harjanto, S. (2020). *Degradation Characterization and Mechanisms of Warm Rolled Mg-1.6Gd with 95% Reduction Ratio for Biodegradable Implant Applications*. 65, 1015–1018. <https://doi.org/10.24425/amm.2020.133209>
- Zhang, Q. W., Lin, L. G., & Ye, W. C. (2018). Techniques for extraction and isolation of natural products: A comprehensive review. *Chinese Medicine (United Kingdom)*, 13(1), 1–26. <https://doi.org/10.1186/s13020-018-0177-x>
- Zulfikar, M., Aryanto, N. C. D., Nur, A. A., & Syafri, I. (2020). Study of Granitoid Distribution at Toboali Waters, Bangka Belitung Province: Seismic data interpretation approach. *Bulletin of the Marine Geology*, 35(2), 53–64. <https://doi.org/10.32693/bomg.35.2.2020.681>